



COTONE 180 UNITO

100% CO

335 gr/mq - H cm 150

Martindale: 32.000 cycles

Colour fastness to light: 5/6

Pilling test: 4/5


Fastness to dry rubbing: 5 / to wet: 5




col. 02



col. 05



col. 01



col. 07



col. 08



col. 25



col. 27



col. 29



col. 30



col. 33



col. 35



col. 36



col. 37



col. 38



col. 39



col. 43



col. 44



col. 45



col. 46



col. 67